

DIN 2401 MALZEME & SICAKLIK BAĞLANTI NORMU

PN	MALZEME				SICAKLIĞA [°C] GORE MAKSIMUM ÇALIŞMA BASINCI [bar]										
	DEMİR DÖKÜM	SFERO DÖKÜM	ÇELİK DÖKÜM	KARBON ÇELİK	20 (120)	200	450	300	350	400	425	450	475	500	
1	GG 25	GGG 40	-	St 37-2	1	-		-							
					1	1	1	1							
2,5	GG 25	GGG 40	-	St 37-2	2,5	-	-	-							
					2,5	2	1,8	1,5							
6	GG 25	GGG 40	-	St 37-2	6	-	-	-							
					6	5	4,5	3,6							
10	GG 25	GGG 40	GS 45	St 37-2	10	-	-	-							
					10	8	7	6							
16	GG 25	GGG 40	GS 45	St 37-2	16	-	-	-							
					16	13	11	10							
	-	-	GS-C 25	C 22 N	16	14	13	11	10	8					
25	-	GGG 38	GS-45.5	C 22 N	25	-	-	-							
			25		20	18	16								
			GS-C 25	25	22	20	17	16	13						
			GS-22 Mo 4	15 Mo 3			25	22	20	19	18	17			
			GS-17 CrMo 55	13 CrMo 44				25	24	23	22	21	20	18	
40	-	-	GS-45.5	C 22 N	40	32	28	24							
			40		-	-	-								
			GS-C 25	40	35	32	28	24	21						
			GS-22 Mo 4	15 Mo 3			40	35	31	30	29	28			
			GS-17 CrMo 55	13 CrMo 44					40	38	36	35	34	33	29
63	-	-	GS-C 25	C 22 N	63	36	29	24							
					63	50	45	40							
					63	-	-	-							
					63	50	45	40	36	32					
			GS-22 Mo 4	15 Mo 3			64	56	50	47	46	45			
			GS-17 CrMo 55	13 CrMo 44					64	61	58	57	56	53	47
100	-	-	GS-C 25	C 22 N	100	80	70	60							
					100	-	-	-							
					100	80	70	60	56	50					
			GS-22 Mo 4	15 Mo 3			100	87	78	74	72	70			
			GS-17 CrMo 55	13 CrMo 44					100	95	91	89	87	82	74
160	-	-	GS-C 25	C 22 N	160	130	112	96							
					160	-	-	-							
					160	130	112	96	90	80					
			GS-22 Mo 4	15 Mo 3			160	139	125	118	115	112			
			GS-17 CrMo 55	13 CrMo 44					160	153	146	142	139	132	118
			-	10 CrMo 9 10											